

# SARENA TEXTILE INDUSTRIES (PVT.) LIMITED

22 Km Sheikupura Road, Lahore Pakistan  
Issue Date Feb 09, 2023



## PRODUCT DATA SHEET

Article Name **Bolan**

Code

### FABRIC DESCRIPTION

Blend	100% Cotton	Count/Construction	20x16/102*58
Finish	FR Proban	Finished Width	61" (ISO 1773)
Dye Class	vat	Weave	3/1 S Twill
Shade		Weight (Gram per meter square)	245 +/- 5% (ISO 12127)


### PERFORMANCE CHARACTERISTICS

PHYSICAL	TEST METHOD	UNIT	RESULTS	REMARKS
Dimensional stability	ISO 15797	%	Warp -3% Weft -3%	
Tensile	ISO 13934-1	N	Warp 1000 min. Weft 500 min.	
Tear	ISO 13937-2	N	Warp 28 min. Weft 26 min.	
Seam slippage	ISO 13936-2	N	Warp <u>6mm@120N</u> Weft <u>6mm@120N</u>	
Pilling	ISO 12945-2	-	4.0	@ 2000 cycles
ph		-	4.5-7.5	

COLOR	TEST METHOD	UNIT	RESULTS	REMARKS
Color fastness to washing	ISO 105 C06 E2S @95°	-	Color Change 4.0 Staining on Cotton 4.0	
Color fastness to perspiration	ISO 105 E04	-	Color Change 4.0 Staining on Cotton 4.0	
Colorfastness to water	ISO 105 E01	-	Color Change 4.0 Staining on Cotton 4.0	
Colorfastness to crocking	ISO 105 X12	-	Dry :3-4~4.0 Wet:3.0	
Colorfastness to light	ISO 105 B02	-	Color Change 4.0	

OTHER	TEST METHOD	UNIT	RESULTS	REMARKS
Fire Retardant	EN ISO 11611	-	Initial: Pass After 50 wash Cycles: Pass	Para 6.7 Procedure A: After 50 wash and dry cycles
Fire Retardant	EN ISO 11612	-	Initial: Pass After 50 wash Cycles: Pass	Para 6.3 Procedure A: After 50 wash and dry cycles
Formaldehyde	ISO 14184-1	-	<75 ppm	

### CARE INSTRUCTIONS



### NOTES:

CHARACTERISTIC MAY VARY WITHIN COMMERCIAL TOLERANCES  
COLOR PERFORMANCE CHARACTERISTIC MAY VARY DEPENDING UPON THE SHADE  
THIS DOCUMENT IS FOR INFORMATION PURPOSE ONLY  
CHEMICAL RESTRICTIONS ARE ACCORDING TO OEKOTEX 100 CLASS II

### Certifications

